



**DC315:** Your one step solution for Polyurethane Foam "15 Minute Thermal Barrier" and "Ignition Barrier" ratings.

**DC315** is a Certified Warnock Hersey listed and rated product which has passed certified testing for both the (UL-1715) 15 minute Thermal Barrier and the NFPA 286 (AC-377 Standards) as an Ignition Barrier.

What is truly amazing is DC315 is an easy to apply new state of the art, water based latex paint. It is as easy to apply as regular latex paint. Using DC315 to satisfy code compliance on "15 Minute Thermal Barriers" and "Ignition Barriers" on your next foam job means:

- ✓ Large single coat spread rate
- ✓ UL 1715 Thermal Barrier – (88.88 sq. ft./gal @ 18 mils wet and 12 mils dry) coverage rate of 1.136 gallons (4.3 L) per 100 square feet (9.3 m<sup>2</sup>)
- ✓ NFPA 286 (AC377) Attic Crawl Space Ignition Barrier - (130 sq.ft./gal @ 12 mils wet 8 mils dry) coverage rate of .77 gallons (2.9 L) per 100 square feet (9.3 m<sup>2</sup>)
- ✓ Reduced labor cost, reduced material cost and higher profits
- ✓ Fast turnaround time
- ✓ Easily applied with a sprayer, brush or roller
- ✓ No complicated mixing -just stir the paint before application
- ✓ No waste
- ✓ Fast and easy clean up of our water based latex product, tools & equipment
- ✓ Will not gum up or block spray equipment
- ✓ Passed strict EPA – VOC and AMQD tests
- ✓ Non Toxic, Low Vapors, Low VOCs
- ✓ No Formaldehyde
- ✓ Two year shelf life
- ✓ Certified Code Compliant Coating



**CERTIFIED APPLICATOR**

Phone: 631.953.6990

Fax: 631.953.6991

[www.idthermal.com](http://www.idthermal.com)

[www.islanddiversified.com](http://www.islanddiversified.com)

1191 Scott Avenue Calverton, New York, 11933

**RECOMMENDED USES:** This product is designed for use on interior polyurethane foam surfaces.

**USED BY:** Schools, Colleges, Nursing Homes, Child Care Centers, Hospitals, Penal Institutions, Apartments, Hotels, Factories, Warehouses, Retail Stores, Restaurants, Utilities, Railroad and other Transportation Companies, Oil and Chemical Installations, Military Installations, and other facilities where fire retardant coatings are required.

**PRECAUTIONS:** Adequate ventilation must be provided during and after application until the coating has dried. Avoid breathing vapors or spray mist. Close container after use.

**Read MSDS before opening containers.**

**SURFACE PREPARATION:** Can be applied directly to fully cured polyurethane foam surfaces. All surface preparation should be carried out in accordance with good painting practices. Remove all loose, peeling or powdery existing paint from the surface. All dirt, grease, oil, wax, and other foreign matter **MUST** be removed with a detergent, rinse surface thoroughly with clear water, and allow drying.

- Application Equipment:** ..... DC315 can be applied by brush, roller or airless sprayer.
- Brushing:** ..... Use top quality polyester/nylon blend brushes such as those supplied by Purdy, Wooster, or equivalent.
- Rolling:** ..... 3/8" polyester blend nap roller covers generally work well.
- Spraying: Pump:** ..... (Graco) for best results use Graco 795 airless sprayer, with a minimum 2000 PSI
- Tip: ..... 526 -529 or equivalent.
  - Filter: ..... 60 Mesh
  - Hose: ..... Use minimum size of 3/8" airless spray line for the first 50' from pump.

**Airless Spray:**

- Fluid Pressure: .....2000 PSI or higher
- Strainer: .....60 Mesh
- Fluid Hose: .....3/8 diameter with a 1/4" whip
- Tip: .....021 - .029

**Conventional Spray**

- Air Supply.....12 CFM, 50 psi at nozzle,
- Fluid.....15 - 20 psi
- Gun. ....Graco 217-800 to 217-816
- Type .....External Mix
- Reduction .....Up to 7%



**CERTIFIED APPLICATOR**  
 Phone: 631.953.6990  
 Fax: 631.953.6991  
[www.idthermal.com](http://www.idthermal.com)  
[WWW.islanddiversified.com](http://WWW.islanddiversified.com)  
1191 Scott Avenue Calverton, New York 11933

**APPLICATION:** Stir thoroughly and apply WFT per test. Do not apply in temperatures below 50°F (10°C).

**CHARACTERISTICS:**

- Finish** .....Flat
- Color**.....Off-White
- Spreading Rate** .....For 15 minute Thermal Barrier (88.88 sq.ft./gal @ 18 mil wet and 12 mils Dry) coverage rate of 1.136 gallons (4.3 L) per 100 Sq ft (9.3 m<sup>2</sup>)
- Spreading Rate**.....For AC377 Attic Crawl Space 130 sq. ft./gal @ 12 mil wet 8 mils Dry) coverage rate of 0.77 gallons (2.9 L) per 100 square feet (9.3 m<sup>2</sup>)
- V.O.C.** .....(47 g/l)
- Volume Solids** .....65%
- Drying Time @ 77°F & 50% RH:** .....To touch 1-2 hours to recoat 2 to 4 hours
- Type of Cure** .....Coalescence
- Flash Point**.....None
- Reducer/Cleaner** .....Water
- Shelf Life** .....2 years (unopened)
- Packaging.** .....1 & 5 gal. Containers
- Shipping weight** .....1 gal - 13 lbs, 5 gals - 58 lbs.
- Application** .....Brush, roller, conventional and airless spray

**FIRE HAZARD CLASSIFICATION:**

DC315 is a certified Warnock Hersey listing and meets all requirements UL1715 15 Minute Thermal Barrier of ICC-ES and NFPA 286 new AC 377 criteria. DC315 passed UL 723 at 0 flame spread index and 10 smoke developed index. DC 315 has done multiple testing and passed multiple foams on all tests. The rooms for the UL 1715 Bay Systems wall insulation to the UL 1715 test room on the back wall, right wall, and ceiling. The walls and ceiling were sprayed with 6 inches of foam. The assembly was made up of 20 gauge metal studs spaced 24 inches oc then 5/8 type X gypsum wallboard was screwed on the inside of the studs. The rooms for the NFPA 286 consisted of three walls with 2x12 studs, 24 inches o.c. and 2x16 joists, 24 inches o.c. with a 1/2 inch gypsum wall board. The final interior dimensions were 8 feet high, 8 feet wide and 12 feet deep. Ceiling joists ran parallel to the short dimension of the room. The corner was constructed such that two studs met at their edges, forming a 90° angle. The spray foam was applied in the stud cavities to a maximum thickness of 12 inches on the walls and 16 inches on the ceiling